

ASTM - AISI THICKNESS TOLERANCE RANGES*

GALVANIZED STEEL SHEETS

Gage No.	Total Coated Thickness (in)		lbs / sq ft	Gage No.	Total Coated Thickness (in)		lbs / sq ft
	Dec Equiv	Toler Range	Weight Equiv°		Dec Equiv	Toler Range	Weight Equiv°
10	0.1382	0.1472 0.1292	5.6379	21	0.0366	0.0406 0.0326	1.5313
11	0.1233	0.1323 0.1143	5.0300	22	0.0336	0.0376 0.0296	1.4063
12	0.1084	0.1174 0.0994	4.4222	23	0.0306	0.0346 0.0266	1.2813
13	0.0934	0.1014 0.0854	3.8103	24	0.0276	0.0316 0.0236	1.1563
14	0.0785	0.0865 0.0705	3.2024	25	0.0247	0.0287 0.0207	1.0313
15	0.0710	0.0770 0.0650	2.8965	26	0.0217	0.0247 0.0187	0.9063
16	0.0635	0.0695 0.0575	2.5905	27	0.0202	0.0232 0.0172	0.8438
17	0.0575	0.0625 0.0525	2.3457	28	0.0187	0.0217 0.0157	0.7813
18	0.0516	0.0566 0.0466	2.105	29	0.0172	0.0202 0.0142	0.7188
19	0.0456	0.0506 0.0406	1.8603	30	0.0157	0.0187 0.0127	0.6563
20	0.0396	0.0436 0.0356	1.6155				

*Gages 10, 11, 12: Tolerances shown for widths over 40" to 60" inclusive.
All other gages: Tolerances shown for widths over 32" to 60" inclusive.

°Based on density of .2833 lbs per cubic inch



**CASCADIA
METALS INC.**